

# STRUCTApanel H2



9mm Structural Panelling



## Product Brochure

STRUCTApanel H2 9mm is made with the same durable resins used in our market leading STRUCTAflor particleboard flooring. STRUCTApanel H2 9mm is a high density panel primarily designed for wall panelling, where it provides high impact resistance compared to alternative lining options, as well as superior screw holding capability. It is treated for termite resistance, and is available as a flat sheet.

**Australian  
PANELS**

[www.australianpanels.com.au](http://www.australianpanels.com.au)



Responsible  
Wood  
www.rw46



PEFC™  
PEFC/21-31-145



# FEATURES

- **High Surface Impact Resistance**  
Superior surface impact resistance compared to plywood and plasterboard
- **Highly durable**  
Made with the same cutting-edge technology & high-quality raw materials as STRUCTAflor
- **High fixing capacity**  
Ability to screw directly into sheet
- **H2 Treated for termite resistance**  
Termite protected particleboard
- **Double-sided**
- **Easy to paint**
- **Multiple joining options**  
H Mould, Cover Strip plus many others
- **Pre-primed/Prefinished**  
Faster project completion

# APPLICATIONS

- Ideal for SIPS manufacture
- Internal lining (sheds/garages)
- Boxes/packaging
- Hoarding
- Dongas
- Schools

**NOTE** As STRUCTApanel H2 9mm Primed is supplied prime-sealed, finish coats can be applied by roller, brush or air spray. Simply apply either solvent or waterborne topcoats in flat or low gloss finishes. Apply as per the paint supplier's instructions. We recommend light sanding between coats.


# SPECIFICATIONS

## Sheet Sizes

- 2440 x 1200 x 9mm
- 2745 x 1200 x 9mm
- 3050 x 1200 x 9mm
- STRUCTApanel H2 9mm Primed is only available in 2440 x 1200 x 9mm

# INSTALLATION

Scan the QR code for installation guide.



## Performance Criteria

Size Tolerances	STRUCTApanel H2 9mm	OSB 9mm	Plywood 9mm	Plasterboard
Density	710kg/m <sup>3</sup>	630kg/m <sup>3</sup>	650kg/m <sup>3</sup>	650kg/m <sup>3</sup>
Thickness Swell (24hrs)	3.5%	11%	-	-
Impact Resistance (Janka)	5030N	3895N	2522N	566N
MOR MPa (Modulus of Rupture)	24	26.7	-	-
MOE MPa	3123	2966	-	-
Lateral Screw Holding* (kg/screw)	87kg	61kg	83kg	28kg
Screw Holding* (kg/screw)	104kg	93kg	95kg	10kg

\*Screw holding test using 30mm x 6-gauge fixings screwed directly to wall panel (not screwed to wall studs).

## Joining Options





Scan the QR code to view  
the full range of products

**Australian  
PANELS**  
[www.australianpanels.com.au](http://www.australianpanels.com.au)

